

Thermo Plastic PVC



SF-PVC

This duct's special molecular bonded construction means less turbulence for maximum flow efficiency

This is a choice duct for many industrial applications, including the transport of particles and gaseous media. Constructed of premium clear PVC this duct allows for continuous visual monitoring.

Novaflex PVC offers

Good resistance to oil, alkali and acids
Extremely flexible with good abrasion resistance

Clear construction for visual monitoring

Specifications

Temperature range: -20°F to +165°F

Lengths: 25 & 50 ft.

Sizes: 1" to 24"

Compression ratio: 2:1

Clear with black external helix. Available with encapsulated wire, or rigid plastic helix. FDA material.

Size ID (in)	Min in. for 90° Bend	Bend Radius	Friction Loss Straight Run 100' (in Wg)	Friction Loss 90° 100' (in Wg)	Positive W.P. (PSIG)	Neg. W.P. (vacuum rating in Hg)	WGT (per foot)	Crush Tests ½ ID (lbs per foot)
2"	8.5"	3.0"	1.78	2.01	18	28	0.47	920
3"	9.5"	3.5"	1.62	1.77	14	28	0.53	740
4"	11.0"	4.5"	1.52	1.66	13.3	24	0.59	520
5"	13.5"	5.0"	1.22	1.34	12.6	19	0.75	410
6"	14.5"	5.5"	1.2	1.32	12	14	0.88	340
8"	19.0"	7.0"	0.74	0.81	10.7	5	1.3	300
10"	21.5"	8.5"	0.68	0.75	7	5	1.55	275
12"	24.0"	9.5"	0.65	0.72	6.3	4	1.75	200

The above data is provided as a general guide only. Friction loss through flexible ducting is dependent on the diameter, length, values, inner wall surface, general duct construction and number of bends. Friction loss values were obtained using 100ft straight runs with an air velocity of 3,500 FPM

All hose and duct manufactured by Novaflex are warranted to be free from all defects in material and workmanship. It is impossible to test Novaflex hose and duct under all conditions to which they might be subjected in the field. It is therefore the buyer and/or end users' responsibility to test all Novaflex hose and duct under conditions that duplicate the service conditions prior to installation.

Berlin, NJ
Indianapolis, IN
Haw River, NC
Whitby, ON

Tel 856.768.2275
Tel 317.334.1444
Tel 336.578.2161
Tel 905.666.4970

Fax 856.768.2385
Fax 317.334.1535
Fax 336-578.5554
Fax 905.666-9388

800.225.0215
800.526.6288
800.334.4270

THE
NOVAFLEX
GROUP
Email: sales@novaflex.com
Website: www.novaflex.com

